



ดูลักซ์ กลอสพีนิช

สีน้ำมันเคลือบเงา สำหรับงานไม้และโลหะ



สีน้ำมันดูลักซ์ เป็นสีเคลือบเงาคุณภาพเยี่ยม ทำจากอัลทิดเรซินสังเคราะห์และผงสีพิเศษ ให้ความปกป้องพื้นผิวและให้ความคงทน มีประสิทธิภาพสูงในการป้องกันเชื้อรา สามารถรักษาความมันเงาไว้ได้นาน ทำความสะอาดได้ง่าย ไม่ผสมสารปรอทและตะกั่ว เหมาะสำหรับการใช้ทาตกแต่ง และปกป้องพื้นผิวไม้และโลหะ ทั้งภายในและภายนอกอาคาร

- फिल्मสีมันเงาสูง ทำความสะอาดง่าย
- มีประสิทธิภาพสูงในการต่อต้านป้องกันและตะไคร่น้ำ
- ไม่ผสมสารตะกั่ว และสารปรอท
- ได้รับการรับรองจากลดคาร์บอนประเภทพิจารณากระบวนการผลิต จากองค์การบริหารจัดการก๊าซเรือนกระจก(องค์การมหาชน) และสถาบันสิ่งแวดล้อมไทย

ข้อมูลทางเทคนิคและคุณสมบัติของฟิล์มสี

ประเภทสี	สีน้ำมันแอลคีด
ลักษณะฟิล์มสี	เงา
ขนาดบรรจุ	¼ และ 1 ยูเอสแกลลอน (สีสำเร็จรูปจากโรงงาน) / 1 และ 3 ลิตร (สีสั่งผสมจากเครื่องผสมสี)
เจดสี	โปรดัคจากแคตตาล็อกสีดูลักซ์ กลอสพีนิช หรือแคตตาล็อกเครื่องผสมสี Dulux Let's Colour
เนื้อสีโดยปริมาตร	30 - 40%
ระยะเวลาแห้งสัมผัส	อย่างน้อย 4 ชั่วโมง
ระยะเวลาทาทับ	อย่างน้อย 8 ชั่วโมง
ระยะเวลาแห้งสมบูรณ์	อย่างน้อย 14 วัน
การครอบคลุมพื้นที่ตามทฤษฎี	40 - 50 ตร.ม. / เที่ยว / แกลลอน
*พื้นที่ครอบคลุมเป็นค่าทางทฤษฎี อาจแตกต่างจากการใช้งานจริงไม่เกิน 20%	

วิธีการใช้งาน

วิธีการใช้งาน	แปรง ลูกกลิ้งขนเรียบ หรือสเปร์รี่
การผสมก่อนใช้งาน	สามารถใช้ได้ทันที หรือเติมน้ำยาผสมสีน้ำมันดูลักซ์ (T850-411) 1 ส่วน ต่อสี 10 ส่วน (ไม่เกิน 10%)
การทำมาสะอาด	ล้างทำความสะอาดอุปกรณ์ด้วย น้ำยาผสมสีน้ำมันดูลักซ์ (T850-411) ทันทีหลังการใช้งาน
การขัดล้างฟิล์มสี	ควรทิ้งให้แห้งอย่างน้อย 14 วัน ก่อนล้างทำความสะอาดได้

ข้อแนะนำในการใช้สีสดเข้ม: อรรถมาติของสีสด มีข้อจำกัดในเรื่องการกลมมิด อาจต้องเพิ่มจำนวนเทียวในการทา หรือใช้สีอ่อนกว่าในเฉดใกล้เคียงกันเป็นสีพื้น

ระบบการทาสี

การเตรียมพื้นผิว สำหรับพื้นผิวไม้

- พื้นผิวไม้ใหม่
- พื้นผิวไม้เก่า

พื้นผิวต้องสะอาดแห้ง ปราศจากขุยไม้ ควันไฟหรือขี้ด ให้เรียบก่อนทาสี เพื่อให้สีซึมเข้าเนื้อไม้ได้ดี ในการฉีกสีเดิมยังอยู่ในสภาพดี ควรขัดด้วยกระดาษทรายละเอียด ให้พื้นผิวมีความหยาบขึ้นอีกเล็กน้อย เพื่อเสริมการยึดเกาะของสีใหม่ให้ดียิ่งขึ้น แต่หากสีเสื่อมสภาพให้ขัดสีเดิมออกให้หมดจนถึงเนื้อไม้ ให้แน่ใจว่าพื้นผิวสะอาดแห้ง ปราศจากขุยไม้ ก่อนทาสีขั้นถัดไป

การทาสีรองพื้น

ทาสีรองพื้นไม้ ดูลักซ์ อลูมิเนียม ฟูด์ไพรมเมอร์ จำนวน 1 เทียว เพื่อป้องกันขุยไม้ และป้องกันน้ำยารักษาเนื้อไม้ไม่ให้ซึมออกมาผสมกับสีทับหน้า จากนั้นทาสีรองพื้นเสริม ดูลักซ์ สปีดอันเดอร์โคท ทับอีกชั้นหนึ่งเพื่อปรับสภาพพื้นผิวไม้ให้เรียบเนียนและเพิ่มความสวยงามของสีทับหน้า

การทาสีทับหน้า

ทาสีทับหน้าด้วย สีดูลักซ์ กลอสพีนิช 2 เทียว ด้วยแปรงทาสี ลูกกลิ้งขนเรียบ หรือสเปร์รี่ โดยทิ้งระยะห่างก่อนทาทับขั้นถัดไปอย่างน้อย 8 ชั่วโมง

การเตรียมพื้นผิว สำหรับพื้นโลหะ

- โลหะใหม่
- โลหะเก่า

ต้องขัดสนิมและล้างคราบไขมันที่เคลือบกันสนิมออก เพื่อช่วยการยึดเกาะของเนื้อสี ในการฉีกสีเดิมยังอยู่ในสภาพดี ควรขัดพื้นผิวให้มีความหยาบ แต่หากสีเสื่อมสภาพให้ขัดสีเดิมและขูดสนิมออกให้หมด

การทาสีรองพื้น

ทาสีรองพื้นโลหะกันสนิม ดูลักซ์ เรดออกไซด์ จำนวน 1 เทียว ทิ้งให้แห้งก่อนทาสีทับหน้า

การทาสีทับหน้า

ทาสีทับหน้าด้วย สีดูลักซ์ กลอสพีนิช 2 เทียว ด้วยแปรงทาสี ลูกกลิ้งขนเรียบ หรือสเปร์รี่ โดยทิ้งระยะห่างก่อนทาทับขั้นถัดไปอย่างน้อย 8 ชั่วโมง



เลข.2625-2557
ผลิตภัณฑ์:
เฉพาะสำหรับงานอาคาร



CMASRI 2016.03.04



ISO 9001 QMS03026/630
ISO 14001 EMS05021/198
OHSAS 18001 OHSAS04016/079
TIS 18001 OHS01013/028

การส่งมอบสีหรือสีรอง: รายละเอียดข้างบนนี้มาจากการทดลอง เพื่อเป็นการแนะนำในการใช้งาน เนื่องจากสีถูกนำไปใช้ในภาวะแตกต่างกัน บริษัทฯจึงไม่สามารถรับประกันใน สิ่งอื่นใดนอกจากคุณภาพของสีเท่านั้น บริษัท อีคโธ โนเบล เทนทิล (ประเทศไทย) จำกัด (ชื่อเดิม บริษัท สี โอ ซี โอ (ประเทศไทย) จำกัด) 34/5 หมู่ 1 ถนนแจ้งวัฒนะ คลองเกลือ ปากเกร็ด นนทบุรี 11120

บริการลูกค้าสัมพันธ์ โทรศัพท์ (662) 572-8888 โทรสาร (662) 572-8889, www.dulux.co.th, www.facebook.co.th/duluxthailand



Dulux Gloss Finish

Alkyd enamel for wood and metal



Dulux Gloss Finish is high quality gloss from alkyd resin and high quality of pigments with excellent durability and outstanding resistance to moulds and fungus attack. Contains no added lead and no added mercury. For the decoration and protection of all interior and exterior building surfaces including, steel, wood etc. Where a durable gloss finish is desired.

- A smooth mirror like finish
- Excellent durability and fungus & fungus resistance
- No added lead and mercury
- It has certified carbon reduction label of production process from Thailand Greenhouse Gas Management Organization and Thailand Environment Institute

Technical Information & Paint Film Properties

Type of Paint	Long Oil Alkyd Enamel Paint
Finish	Gloss
Pack size	¼ and 1 U.S.Gallon (Ready-mixed), 1 and 3 Litres (Tinting)
Colour Offer	Please refer Dulux Dulux colour card and Dulux Let's Colour fandeck
Volume Solids	30 - 40%
Touch Dry	At least 4 hour
Recoat Dry	At least 8 hour
Full Cure	At least 14 days
Theoretical Coverage	40 – 50 Sq.m./coat/gallon

*Coverage is theoretical value and may differ from real application +-20%

Application

Application Method	Brush, Short Hair Roller or Spray
Mixing Ratio	Ready to use. Can be thinned with 1 part of Dulux Quick Cut Solvent (T850-411) to 10 parts of the product (10%)
Cleaning Up	Clean all equipments with Dulux Quick Cut Solvent (T850-411) immediately after used
Washing Instructions of painted wall	Allow at least 14 days from application before cleaning.

Processes for strong colours : Vibrant/deep shades may require additional coats /or apply softer colour of the same shade as undercoat

Application System

Surface Preparation : Wooden Surface

- *New wood*
Surface must be clean, dry and free from all defective or poorly adhering materials, dirt, grease, wax, etc. All surfaces should be rubbed down for good penetration of top coat paint.
- *Old wood*
If previous paint is in good condition, rub down with abrasive paper for good adhesion of new paint. If surface is defective or friable, thoroughly rub down until previous paint is totally removed. Ensure that surface is clean, dry and free from all defective or poorly adhering materials, dirt, grease wax, etc. Before painting.

Priming
Apply 1 coat of Dulux Aluminum Wood Primer to prevent bleeding from underneath. Then, for perfectly smooth film and cost saving of primer, apply 1 coat of Dulux Speed Undercoat.

Coating
Apply 2 coats of Dulux Gloss Finish with roller or spray. Allow 6 hours drying between coats.

Surface Preparation : Metal Surface

- *New metal*
Remove all corrosive and dirt for good penetration of top coat paint.
- *Old metal*
If previous paint is in good condition, rub down with abrasive paper for good adhesion of new paint. If surface is defective, thoroughly rub down till old paint and corrosive totally removed.

Priming
Apply 1 coat of Dulux Red Oxide Metal Primer. Allow 6 hours drying prior applying top coat.

Coating
Apply 2 coats of Dulux Gloss Finish with brush, short hair roller or spray. Allow 6 hours drying between coat.



ISO 9001 QMS03026/630
ISO 14001 EMS05021/198
OHSAS 18001 OHSAS04016/079
TIS 18001 OHS01013/028

The information in this datasheet is given to the best of our knowledge based on laboratory testing and for use recommendation. As the product is often used under conditions beyond our control, the company cannot guarantee anything only the quality of the product.

AkzoNobel Paints (Thailand) Ltd. (Former ICI Points (Thailand) Ltd.) 34/5 Moo 1 Choeng Watana Road, Klongklue, Pakkred Nonthaburi 11120
Customer Service : Telephone (662) 572-8888 Fax (662) 572-8889. www.dulux.co.th, www.facebook.com/duluxthailand