

<b>FEATURES</b>	<p>TOA SHIELD-1 Nano Emulsion paint for Interior. The high quality 100% acrylic emulsion a combination of rutil titanium pigment blended with a fungal inhibitor .It gives performance of good hiding , good coverage and washability. It contains no added lead and mercury.</p> <p>Typical Use ; It is ideal for application to interior concretes, new and old masonry surfaces, plasters, bricks, asbestos shingled and siding.</p>
<b>TECHNICAL INFORMATION</b>	<p>Type 100% Pure Acrylic Emulsion Paint</p> <p>Color Wide range of colors. Please refer to colour card.</p> <p>Film appearance Matt</p> <p>Solid by volume 34-36 %</p> <p>Solid by weight 53-55 %</p> <p>Flash point N/A °C</p> <p>Volatile organic compounds (VOCs) less than 10 gram / litre</p> <p>Wet film thickness 100-110 microns</p> <p>Dry film thickness 35-40 microns</p> <p>Theoretical coverage. 35-40 sq. meter / gallon / coat</p> <p>Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.</p> <p>Touch dry ( 25-30°C) 30 minutes</p> <p>Recoat dry ( 25-30°C) 2 hours</p> <p>Full cure ( 25-30°C) 7 days</p>
<b>REFERENCE STANDARD</b>	<p>TIS 2321-2549(2006)(Weather Resistant Emulsion Paints),</p> <p>Green Label Thailand</p>
<b>APPLICATION</b>	<p>Tools Roller, Brush, Spray</p> <p>Diluent Clean Water</p> <p>Dilution (%) 10-15 % ( roller and brush )</p> <p>15-20 % ( spray )</p>
<b>APPLICATION SYSTEM</b>	<p><b>Surface Preparation</b></p> <p><b>Old surface</b> Powdery and chalky surface must be scrubbed and cleaned with water Fungus and mildew growth must be cleaned off before applying microkill. Left to dry for 2-3 days Apply on cracks with TOA Acrylic Filler for the crack width &lt; 1 mm. and not to crack continuously Apply on cracks with TOA Acrylic Sealant for the crack width &gt; 1 mm. and crack continuously</p> <p><b>New surface</b> Substrate must be completely cured and dried ( ~ 1 month ) free from oil ,grease ,mildew, from release agents and foreign matters. or measure moisture which should be less than 14% on surface with protimeter mini If any crack, it should be repaired on surface before applying</p>



## Coating system

Primer For Old Surface  
Primer For New Surface  
Topcoat

Apply 1 coat of TOA CONTACT PRIMER  
Apply 1 coat of TOA SHIELD-1 NANO ALKALI RESISTING PRIMER  
Apply 2-3 coats of TOA SHIELD-1 NANO MATT FOR INTERIOR

\*\* Recommend for deep tone , you should apply middle coat that it has tone lighter before requiring color

## HANDLING AND STORAGE

Storage condition

: The product must be stored in accordance with national regulations.  
Keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.  
Containers must be kept tightly closed.

Shelf life

: 5 years at 30-35 °C.

## HEALTH AND SAFETY

: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

: For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

## DISCLAIMER

: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.

คุณสมบัติ	สีน้ำคุณภาพสูง ผลิตจากสารอะคริลิก 100% พร้อมเม็ดเกรดและผงสีพิเศษผสมสารป้องกันเชื้อรา เพื่อปกป้องผิวได้ยาวนาน อีกทั้งให้การกลบพื้นผิวและครอบคลุมพื้นผิวได้มาก ทำให้ฟิล์มเรียบเนียนสวย ปราศจากสารปรอทและสารตะกั่ว ไม่เป็นอันตรายต่อผู้ใช้และผู้อยู่อาศัย การใช้งาน เหมาะสำหรับทาตกแต่งบนพื้นผิวปูนฉาบ กระเบื้องแผ่นเรียบ คอนกรีต หรือพื้นผิวอื่น ๆ ที่มีลักษณะเดียวกัน เหมาะสำหรับงานภายในอาคาร
ข้อมูลทางเทคนิค	สีน้ำทาอาคารจากเนื้ออะคริลิกแท้ 100% สามารถเลือกได้จากเวดสีในแคตตาล็อกและเครื่องผสมสีอัตโนมัติ ชนิดด้าน เนื้อสีโดยปริมาตร 34-36 % เนื้อสีโดยน้ำหนัก 53-55 % จุดวาบไฟ N/A °C ปริมาณสารอินทรีย์ระเหยได้ น้อยกว่า 10 กรัม ต่อ ลิตร ความหนาฟิล์มสีเมื่อเปียก 100-110 ไมครอน ความหนาฟิล์มสีเมื่อแห้ง 35-40 ไมครอน การครอบคลุมพื้นที่ตามทฤษฎี 35-40 ตารางเมตร ต่อ แกลลอน ต่อ เที่ยว หมายเหตุ : การผสม, การใช้งาน, ความหยาบและรูพรุนของพื้นผิว มีผลต่อการการปกคลุมพื้นผิว ระยะเวลาแห้งสัมผัส (อุณหภูมิ 25-30°C) 30 นาที ระยะเวลาแห้งทาทับ (อุณหภูมิ 25-30°C) 2 ชั่วโมง ระยะเวลาแห้งสมบูรณ์ (อุณหภูมิ 25-30°C) 7 วัน
มาตรฐานอ้างอิง	มาตรฐานอุตสาหกรรม 2321-2549 (สีอิมัลชันทนสภาวะอากาศ) ฉลากเขียวไทย
วิธีใช้งาน	อุปกรณ์ แปรงทาสี เครื่องพ่น ตัวเจือจาง น้ำสะอาด การเจือจาง (%) 10-15 % (กลิ้ง หรือ ทา) 15-20 % (พ่น)
ระบบการใช้งาน	การเตรียมพื้นผิว พื้นผิวเก่า ขัดล้างสีเดิมที่เสื่อมสภาพออกให้หมด (ไม่ควรใช้แปรงลวด) บริเวณที่มีเชื้อราหรือตะไคร่น้ำขัดล้างด้วยน้ำยาฆ่าเชื้อรา TOA Microkill ล้างทำความสะอาด แล้วทิ้งให้แห้ง 1-2 วัน บริเวณที่มีรอยแตกร้าวความกว้างน้อยกว่า 1 มิลลิเมตรและไม่แตกต่อเนื่อง ให้อุดโป๊วด้วยทีโอเอ อะคริลิก ฟิลเลอร์ บริเวณที่มีรอยแตกร้าว ความกว้างมากกว่า 1 มิลลิเมตรหรือมีการแตกต่อเนื่อง ให้อุดโป๊วด้วย ทีโอเอ อะคริลิก ซิลแลนท์ พื้นผิวใหม่ ทิ้งให้ผนังแห้งอย่างน้อย 1 เดือน หรือเช็คความชื้นที่พื้นผิวมีค่าไม่เกิน 14% วัดด้วยเครื่อง Protimeter Mini หากพื้นผิวมีรอยแตกร้าว ไม่เรียบ แนะนำให้ทำการซ่อมแซมรอยแตกร้าวหรือฉาบแต่งผิว ก่อนการทาสี ด้วยวัสดุอุดโป๊ว หรือฉาบแต่งผิว ที่เหมาะสม ทำความสะอาดผนังให้ปราศจากเศษฝุ่นผง เศษซีเมนต์ และคราบไขมัน
ระบบการทาสี	

สีรองพื้นสำหรับพื้นผิวเก่า สีรองพื้นสำหรับพื้นผิวใหม่ สีทับหน้า	ทาสีรองพื้นปูนกับสีเก่า ทีโอเอ คอนแทค โพรเมอร์ จำนวน 1 เที่ยว ทาสีรองพื้นปูนใหม่กับสีเก่า ทีโอเอ ซิลด์ วัน นาโน จำนวน 1 เที่ยว ทาสีทับหน้าด้วยสีน้ำทีโอเอ ซิลด์ วัน นาโน ชนิดด้านสำหรับภายในจำนวน 2-3 เที่ยว ในกรณีสีเข้มสด ให้ใช้เฉดสีที่อ่อนกว่าทาในเที่ยวแรก แล้วจึงทาเฉดสีที่ต้องการกับ 1-2 เที่ยว
การเก็บรักษา สภาวะการเก็บรักษา อายุผลิตภัณฑ์	: จัดเก็บสินค้าในที่แห้ง มีอากาศถ่ายเทดี ปิดฝาให้สนิท ให้แน่นตลอดเวลา ไม่ควรเก็บในที่ร้อนและไม่ให้ถูกแสงแดดโดยตรง : 5 ปี ที่อุณหภูมิ 30-35 องศาเซลเซียส
ข้อมูลสุขภาพและความปลอดภัย	: กรุณาดูข้อควรระวังที่ติดไว้บนภาชนะบรรจุ การทำงานสีควรทำในที่ที่อากาศถ่ายเทสะดวก ควรใส่หน้ากากเมื่อทำการพ่นสีและพยายามเลี่ยงมิให้สัมผัสผิวหนัง หรือสูดดม ถ้าสีหกใส่ผิวหนังควรล้างด้วยน้ำสะอาดกับสบู่ทันที ถ้าสีเข้าตาควรล้างด้วยน้ำสะอาดทันทีและ รีบไปพบแพทย์ : รายละเอียดด้านความปลอดภัยเกี่ยวกับการใช้ผลิตภัณฑ์ ระบุไว้ในข้อมูลด้านความปลอดภัย
การสงวนสิทธิ์เรียกร้อง	: รายละเอียดข้างบนนี้ได้มาโดยการทดลอง และจากประสบการณ์ที่ผ่านมา เนื่องจากสีถูกนำไป ใช้ในสภาวะแตกต่างกันเราจึงไม่สามารถรับประกันในสิ่งอื่นใดนอกจากคุณภาพของสีเท่านั้น <b>บริษัทขอสงวนสิทธิ์ที่จะเปลี่ยนแปลงข้อมูลโดยมีต้องแจ้งล่วงหน้า</b>